

JENSEN SURE SEAL HAND HELD PORTABLE HEAT SEALER

Model JSS-500

Heat Seal Test Results

Seal Time = 3 seconds

Seal Quality: A = Acceptable, U = Un-acceptable

Yellow Box = Optimum Setting

Material	175°F	200°F	225°F	250°F	275°F	300°F	325°F	350°F	375°F	400°F	425°F
4 mil LLDPE (.004")	U	U	U	A	A	U	U	U	U	U	U
48ga METPET / 4mil LLDPE (.0045")	U	U	A	A	A	A	A	A	A	U	U
CadPak-PL (.0032")	U	U	U	U	A	A	A	A	A	U	U
CadPak-N (.0042")	U	U	U	U	U	A	A	A	A	U	U
CadPak-HD100 (.0079")	U	U	U	U	U	U	A	A	A	A	A
BPN-700 (.007")	U	U	U	U	U	A	A	A	A	A	U
CadPak-HD200 (.0103")	U	U	U	U	U	U	U	A	A	A	A

Note: These tests were performed with the equipment used in the intended upon fashion which is with manual pressure applied to the handles. Depending upon who performs the sealing operation, slightly different results could be obtained. It is recommended to do some test sampling using this chart as a guide to a starting point.

